

PATENT APPLICATION
Docket No.: NC 82,621

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application.

1. (currently amended) A method for creating a microarray of biomaterial comprising the steps of:
 - providing one or more sources of laser energy that produce laser energy;
 - providing a receiving substrate;
 - wherein the receiving substrate is positioned opposite the source of laser energy;
 - providing a target substrate;
 - wherein the target substrate is positioned between the receiving substrate and the source of laser energy;
 - wherein a gap exists between the receiving substrate and the target substrate;
 - wherein the target substrate comprises a laser-transparent support and a composite material;
 - wherein the laser-transparent support has a laser-facing surface facing the source of laser energy;
 - wherein the laser-transparent support has a support surface facing the receiving substrate;
 - wherein the composite material has a back surface in contact with the support surface;
 - wherein the composite material has a front surface facing the receiving substrate;
 - wherein the composite material comprises a matrix material and a transfer material;
 - wherein the transfer material comprises biomaterial; and
 - wherein the matrix material has the property of being desorbed from the laser-transparent support when exposed to the laser energy.
- positioning the source of laser energy in a spaced relation to the target substrate so that the laser energy will strike the composite material at a defined target location;
- positioning the receiving substrate in a spaced relation to the target substrate;
- exposing the target substrate to the laser energy;

PATENT APPLICATION
Docket No.: NC 82,621

- wherein the laser energy is directed through the laser-facing surface and through the laser-transparent support to strike the composite material at the support surface-back surface interface at the defined target location;
- wherein the laser energy has sufficient energy to cause the desorption of the composite material from the support surface; and
- wherein the desorbed composite material is deposited at a defined receiving location on the receiving substrate to form a deposited composite material;
- and
- repeating the steps of positioning the source of laser energy, positioning the receiving substrate, and exposing the target substrate at successive defined target locations and successive defined receiving locations such that the composite material is deposited as a microarray of deposited composite material.
2. (original) The method of claim 1, wherein the method is controlled by a computer.
 3. (original) The method of claim 1,
 - wherein the steps are carried out at about room temperature; and
 - wherein the steps are carried out at about atmospheric pressure.
 4. (original) The method of claim 1, wherein the steps are carried out under one or more controlled conditions selected from the group consisting of humidity, atmospheric composition, air pressure, temperature, sterility.
 5. (original) The method of claim 1, wherein the source of laser energy is a pulsed laser.
 6. (original) The method of claim 1, wherein the laser energy is focussed through an objective.
 7. (original) The method of claim 1, wherein the steps of positioning the source of laser energy and positioning the receiving substrate are achieved through the use of one or more positioning means selected from the group consisting of a laser positioning means, a target substrate positioning means, and a receiving substrate positioning means.

PATENT APPLICATION
Docket No.: NC 82,621

8. (original) The method of claim 1 comprising the following additional steps performed before the step of providing a target substrate:
positioning the receiving substrate in a spaced relation to the source of laser energy; and
exposing the receiving substrate to the laser energy so that the laser energy machines
away a defined machining location on the receiving substrate.
9. (original) The method of claim 8, wherein the defined machining location comprises a via through the receiving substrate.
10. (original) The method of claim 8, wherein the composite material is deposited into a defined machining location that has been previously machined away by the laser energy.
11. (original) The method of claim 1 comprising the following additional steps after the step of exposing the target substrate:
removing the target substrate from its position between the source of laser energy and the
receiving substrate;
positioning the receiving substrate in a spaced relation to the source of laser energy; and
exposing the receiving substrate to the laser energy so that the laser energy machines
away a defined machining location on the receiving substrate or on the deposited
composite material.
12. (original) The method of claim 11, wherein the defined machining location comprises a via through the receiving substrate.
13. (original) The method of claim 1,
wherein the step of providing a target substrate is repeated one or more times
using target substrates comprising different composite materials; and
wherein the different composite materials are deposited in respective patterns on
the receiving substrate.
14. (original) The method of claim 13, wherein the different composite materials comprise different transfer materials.

PATENT APPLICATION
Docket No.: NC 82,621

15. (original) The method of claim 13,
wherein one or more composite materials comprise a matrix material and an
electronic transfer material; and
wherein one or more electronic transfer materials are used to create electronic
circuitry on the receiving substrate.
16. (original) The method of claim 15, wherein the one or more electronic transfer materials
are independently selected from the group consisting of metal, dielectric, resist,
semiconductor, and combinations thereof.
17. (original) The method of claim 1, wherein the laser-transparent support comprises quartz
or machine etched quartz.
18. (original) The method of claim 1, wherein the laser-transparent support comprises a laser-
transparent flexible polymer ribbon.
- 19-20. (cancelled)
21. (original) The method of claim 1, wherein the receiving substrate comprises a non-planar
surface.
22. (original) The method of claim 1, wherein the receiving substrate comprises one or more
materials selected from the group consisting of chemically functionalized glass, polymer-
coated glass, quartz, natural hydrogel, synthetic hydrogel, uncoated glass, nitrocellulose
coated glass, silicon, glass, plastics, metals, and ceramics.
23. (original) The method of claim 1, wherein the receiving substrate comprises
functionalization selected from the group consisting of covalent functionalization,
physisorbed functionalization, and combinations thereof.

PATENT APPLICATION
Docket No.: NC 82,621

24. (original) The method of claim 23, wherein the functionalization is selected from the group consisting of a living host, a living cell, a living cell culture, a non-living cell, a non-living group of cells, a living tissue, a chemically functionalized surface, and a biologically functionalized surface.
25. (original) The method of claim 1, wherein the biomaterial is living or active.
26. (original) The method of claim 25, wherein the living or active biomaterial remains living or active on the receiving substrate.
27. (original) The method of claim 1, wherein the biomaterial comprises one or more materials selected from the group consisting of DNA, portions of DNA strands, and RNA.
28. (original) The method of claim 1, wherein the biomaterial comprises protein.
29. (original) The method of claim 1, wherein the biomaterial comprises a layer of stained or fixed tissue.
30. (original) The method of claim 1, wherein the biomaterial comprises a layer of living tissue.
31. (original) The method of claim 1, wherein the biomaterial comprises one or more functional supporting media selected from the group consisting of nutrients, and other life supporting material.
32. (original) The method of claim 1, wherein the composite material is at about the incubation temperature of the biomaterial.

PATENT APPLICATION
Docket No.: NC 82,621

33. (original) The method of claim 1, wherein the matrix material comprises one more materials selected from the group consisting of glycerol, water, polymer, natural hydrogel, synthetic hydrogel, surfactant, dimethylsulfoxide, water/dimethylsulfoxide mixture, nitrocellulose gel, sol gel, and ceramic composite.
34. (original) The method of claim 1, wherein the matrix material comprises a mixture of water and glycerol.
35. (original) The method of claim 1, wherein the composite material is frozen to the laser-transparent support.
36. (original) The method of claim 1, wherein the composite material is at a temperature of from about -50°C to about 100°C.
37. (original) The method of claim 1, wherein the microarray comprises one or more materials selected from the group consisting of DNA, portions of DNA strands, and RNA.
38. (original) The method of claim 1, wherein the microarray is a protein microarray.
39. (original) The method of claim 38, wherein the protein microarray can be used to analyze protein-protein, protein-DNA, and protein-RNA interactions.
40. (original) The method of claim 1, wherein the microarray can be used to identify biomolecules.
41. (original) The method of claim 1, wherein the microarray comprises portions of a layer of tissue.
42. (original) The method of claim 41, wherein the microarray is a living tissue microarray.
43. (original) The method of claim 41, wherein the tissue is stained or fixed.

PATENT APPLICATION
Docket No.: NC 82,621

44. (original) The method of claim 41, wherein the tissue comprises tissue removed from more than one organism.